

Expertise:

1507105-01/02-00-01e

Datum / Date: 2015-08-27
LV/DD/ke

Client: Nemes, Vincenz GmbH & Co. KG, Belruptstraße 20, AT-6900 Bregenz

Order: Examination of materials

Order: 2015-08-20 Mr. Nemes

Receipt: 2015-08-24

Test item:

- 15 07105 01 Material sample, article Kansas black + fleece 120g/qm black + 9050 hydro
(mat. no. 03/00/127 0002 black)
- 15 07105 02 Material sample, article Kansas black + Silon F404/22/400g/2,2 mm anthracite + 9050 hydro
(mat. no. 03/00/126 0002 black)

Results of examination:

1507105-01-00-01 mat. no. 03/00/127 0002 black

Mass per unit area using small samples

DIN EN 12127


| Parameter | Unit | Result | Requirement of client | Assessment | |
|----------------|------------------|--------|-----------------------|------------|--------|
| | | | | passed | failed |
| Normal climate | g/m ² | 390,7 | 369 - 451 | X | |

1507105-02-00-01 mat. no. 03/00/126 0002 black

Mass per unit area using small samples

DIN EN 12127

| Parameter | Unit | Result | Requirement of client | Assessment | |
|----------------------------|------------------|--------|-----------------------|------------|--------|
| | | | | passed | failed |
| Normalklima Normal climate | g/m ² | 670,4 | 648 - 792 | X | |



Dipl.-Ing. (FH) L. Vjselaar
(Abteilungsleitung / Department Management)



Dr. K. Schulte
(Institutsleitung / Managing Director)



Die Prüfergebnisse beziehen sich ausschließlich auf die Prüfgegenstände. Ohne schriftliche Genehmigung des PFI darf die Expertise nicht auszugsweise verwendet werden. Restliches Untersuchungsmaterial wird nach 10 Wochen vernichtet. In Einzelfällen kann eine Untervergabe an andere geeignete Prüflaboratorien erfolgen. Ein Verzeichnis der akkreditierten Prüfverfahren und unsere geltenden Allgemeinen Geschäftsbedingungen können auf unserer Internetseite eingesehen werden und werden Ihnen auf Anfrage gerne zugesandt. / Test results solely refer to the items tested. Extracts of the expertise may not be used without written permission by PFI. Remaining materials will be destroyed after 10 weeks. In individual cases, tests can be carried out by qualified subcontracting laboratories. A list of accredited test methods and our applying general terms and conditions are available on our website and will be sent to you on request.

Prüf- und Forschungsinstitut Pirmasens e.V. • Marie-Curie-Strasse 19 • D-66953 Pirmasens • www.pfi-pirmasens.de • info@pfi-pirmasens.de